KASTURI				RABOND [®]	
Steelwool Grade K-0234 Specification Sheet					
MATERIAL	Steelwool Fiber Grade K-0234			SAFETY INSTRUCTIONS	
APPEARANCE	Metallic Grey ; Oil Free Fibers			The use of gloves and eye protection during handling	
DESCRIPTION	Steelwool chopped to short fiber length			of fibers is strongly advised.	
MATERIAL PROPERTIES					
(%)		C: 0.13 – 0.18 Mn: 0.80 – 1.10			
		Si: 0.10 Max			
		P: 0.06 – 0.09			
			S: 0.03	5 Max	
Physical Properties:					
Specific gravity (g/ccm)		7.6 to 8.2			
Loose Bulk Density		0.60 to 0.77			
Acetonic extract (%)		0.05 max			
Sieve Analysis:					
Sieve No. (B.S.S)		% Of Wt Retained			
+22 BSS		0			
-22 +44 BSS		0 - 4			
-44+100 BSS		23 - 43 22 - 42			
– 100 +200 BSS – 200 (Pan)		22 - 42 23 - 43			
Packing: Non-woven sacks with inner lining of 25 Kgs		Storage: Keep it covered and in a dry shelf.			
www.steelfiberindia.in		Register Amravat	Diffice I METAL COMPOSITE ed Office A-30/3/1, N i, Maharashtra, India : 444605	AIDC Floor, Office No. S-1063A, Janta	