





Steelwool Grade K 18 **Specification Sheet**

MATERIAL

Steelwool Fiber Grade K18

APPEARANCE

Metallic Grey; Oil Free Fibers

DESCRIPTION

Steelwool chopped to short fiber length

SAFETY INSTRUCTIONS

The use of gloves and eye protection during handling of fibers is strongly advised.

MATERIAL PROPERTIES



Chemical Composition:

(%)	C: 0.07 - 0.12
	Mn: 0.30 - 1.00
	Si: 0.08 - 0.15
	P: < 0.05
	S: < 0.05

Physical Properties:

Specific gravity (g/ccm)	7.6 to 8.2
Loose Bulk Density	0.80 – 1.20
Acetonic extract (%)	0.5 max

Sieve Analysis:

Sieve No. (B.S.S)	% Of Wt Retained
+ 44 BSS	5 ~ 15
- 44 + 85 BSS	10 ~ 20
- 85 +100 BSS	10 ~ 25
- 100 +200 BSS	25 ~ 40
- 100 (Pan)	25 ~ 35

Packing: Storage:

Non-woven sacks with inner lining of 25 Kgs	Keep it covered and in a dry shelf.

Head Office

KASTURI METAL COMPOSITE LTD Registered Office A-30/3/1, MIDC Amravati, Maharashtra, India -

Pincode: 444605

Mumbai Office

Akshar Business Park, S Wing, First Floor, Office No. S-1063A, Janta Market Road, Sector-25, Vashi, Navi Mumbai-400703.