KASTURI				RABOND <sup>®</sup>	
			ool Grade K-20N fication Sheet SAFETY INSTRUCTIONS The use of gloves and eye protection during handling		
DESCRIPTION	Steelwool chopped to short fiber length			of fibers is strongly advised.	
Chemical Composition:					
(%)		C : 0.07 - 0.12 Mn : 0.30 - 1.00			
		Si : 0.08 - 0.15			
		P:<0.05			
		S : < 0.05			
Physical Properties:					
Specific gravity (g/ccm)		7.6 to 8.2			
Loose Bulk Density		0.70 – 1.10			
Tapped Bulk density			0.90 – 1.60		
Acetonic extract (%) 0.2% max					
Sieve Analysis: Sieve No. (B.S.S )		% Of Wt Retained			
+18 BSS		NIL			
-18 +36 BSS		10 Max			
-36 + 100 BSS		20 - 40			
– 100 ( Pan)		50 - 70			
Packing:		Storage:			
Non-woven sacks with inner lining of 25 Kgs		Keep it covered and in a dry shelf.			
www.steelfiberindia.in		Registe Amravat	Dffice I METAL COMPOSITE red Office A-30/3/1, I i, Maharashtra, India : 444605	MIDC Floor, Office No. S-1063A, Janta	