KASTURI				RABOND [®]	
Steelwool Grade K-22 Specification Sheet					
MATERIAL	Steelwool Fiber Grade K-22			SAFETY INSTRUCTIONS	
APPEARANCE	Metallic Grey ; Oil Free Fibers			The use of gloves and eye protection during handling	
DESCRIPTION	Steelwool chopped to short fiber length			of fibers is strongly advised.	
MATERIAL PROPERTIES					
Chemical Composition: C : 0.07 - 0.12					
(%)		Mn : 0.60 – 1.00			
		Si : 0.08 - 0.15			
		P:<0.05			
			S : < 0.05		
Physical Properties:					
Specific gravity (g/ccm) Loose Bulk Density		7.6 to 8.2 0.70 – 1.00			
Acetonic extract (%)		0.20% max			
Sieve Analysis:					
Sieve No. (B.S.S)		% Of Wt Retained			
+ 16 BSS		0~1			
	- 16 + 36 BSS		0~5		
- 36 + 60 BSS		5~ 15			
- 60 + 100 BSS		10 ~ 20			
- 100 + 200 BSS - 200 (Pan)		12~ 30 29 ~ 73			
Packing:		Storage:			
Non-woven sacks with inner lining of 25 Kgs		Keep it covered and in a dry shelf.			
www.steelfiberindia.in		Registe Amrava	Dffice RI METAL COMPOSITE red Office A-30/3/1, N ti, Maharashtra, India 1 : 444605	MIDC Floor, Office No. S-1063A, Janta	