





Steelwool Grade K-0394 **Specification Sheet**

MATERIAL

Steelwool Fiber Grade K-0394

SAFETY INSTRUCTIONS

APPEARANCE

Metallic Grey; Oil Free Fibers

The use of gloves and eye protection during handling of fibers is strongly advised.

DESCRIPTION

Steelwool chopped to short fiber length

MATERIAL PROPERTIES



Chemical Composition:

(%)	C: 0.10 max
	Mn: 0.55 max
	Si: 0.15-0.30
	P: 0.015 max
	S: 0.030 max

Physical Properties:

Specific gravity (g/ccm)	7.6 to 8.2
Loose Bulk Density	1.00 – 1.30
Acetonic extract (%)	0.15 max

Sieve Analysis:

Sieve No. (B.S.S)	% Of Wt Retained
+18 BSS	2 Max
-18 +30 BSS	10 Max
-30 + 60 BSS	15 - 35
- 60 +100 BSS	10 - 35
-100 + 200	20 - 50
- 200 (Pan)	20 Max

Packing: Storage:

Keep it covered and in a dry shelf. Non-woven sacks with inner lining of 25 Kgs

Head Office

KASTURI METAL COMPOSITE LTD Registered Office A-30/3/1, MIDC Amravati, Maharashtra, India -Pincode: 444605

Mumbai Office

Akshar Business Park, S Wing, First Floor, Office No. S-1063A, Janta Market Road, Sector-25, Vashi, Navi Mumbai-400703.