| KASTURI                               |   |                                    |   | RABOND  |  |
|---------------------------------------|---|------------------------------------|---|---|--|
|                                       |   |                                    | l Grade<br>fication   | RB-264 K<br>Sheet                                     |  |
| MATERIAL S                            | Steel wool Fiber Grade RB-264 K         |                                    | SAFETY INSTRUCTIONS   |   |  |
| APPEARANCE                            | Metallic Grey ; Oil Free Fibers         |                                    |   | The use of gloves and ey<br>protection during handlir |  |
| DESCRIPTION St                        | Steelwool chopped to short fiber length |                                    |   | of fibers is strongly advis                           |  |
| Chemical Composition:                 |   |                                    | C: 0.07   |   |  |
| (%)                                   |   | Mn: 0.30 - 1.00<br>Si: 0.08 - 0.15 |   |   |  |
|                                       |   | P: < 0.05                          |   |   |  |
|                                       |   |                                    | S: < (  |   |  |
| Physical Properties:                  |   |                                    |   |   |  |
| Specific gravity (g/ccm)              |   | 7.6 to 8.2                         |   |   |  |
| Loose Bulk Density                    |   | 0.55 – 0.85                        |   |   |  |
| Tapped Bulk density                   |   | N/A                                |   |   |  |
| Acetonic extract (%                   | )                                       |                                    | 0.5 ו   | max   |  |
| Sieve Analysis:<br>Sieve No. (B.S.S ) |   | % Of Wt Retained                   |   |   |  |
| + 30 BSS                              |   | 5.0 Max                            |   |   |  |
| - 30 + 60 BSS                         |   | 10~ 20                             |   |   |  |
| - 60 + 120 BSS                        |   | 20 ~ 30                            |   |   |  |
| – 120 ( Pan)                          |   | 30 ~ 60                            |   |   |  |
| Packing:                              |   |                                    | Stor  | age:  |  |
| Non-woven sacks with inner li         | ning of 25 Kgs                          | Кеер                               | it covered  | and in a dry shelf.                                   |  |
|                                       |   | Registe                            | Office<br>Il METAL COMPOSIT<br>red Office A-30/3/1,<br>i Mabarashtra Indi | MIDC Floor, Office No. S-1063A, Jan                   |  |

www.steelfiberindia.in

KASTURI METAL COMPOSITE LTD Registered Office A-30/3/1, MIDC Amravati, Maharashtra, India -Pincode : 444605

Akshar Business Park, S Wing, First Floor, Office No. S-1063A, Janta Market Road, Sector-25, Vashi, Navi Mumbai-400703.